

MOTIVE J305-AES

MODEL J305-AES

VOLTAGE 6

CAPACITY 279Ah @ 20Hr MATERIAL Polypropylene

BATTERY VRLA AGM / Non-Spillable / Maintenance-Free

COLOR Maroon

WATERING No Watering Required





6 VOLT

PHYSICAL SPECIFICATIONS

| BCI | MODEL NAME | TERMINAL TYPE | DIMENSIONS © INCHES (mm) | | WEIGHT LBS. (kg) | HANDLES | INSTALLATION ORIENTATION | |
|-----|------------|---------------|--------------------------|-------------|------------------|--------------|--------------------------|------------|
| | | | LENGTH | WIDTH | HEIGHT F | | | Horizontal |
| 902 | J305-AES | | | 14.09 (358) | 101 (45) | Braided Rope | and Vertical | |

ELECTRICAL SPECIFICATIONS

| VOLTAGE | CRANKING PE | ERFORMANCE | CAPACITY A MINUTES | | CAPACITY ^B AMP-HOURS (Ah) | | | | ENERGY (kWh) | INTERNAL RESISTANCE (mΩ) | SHORT CIRCUIT CURRENT (amps) |
|---------|--------------------------|-------------------------|--------------------|-----------|--------------------------------------|-------|-------|--------|--------------|--------------------------|------------------------------|
| 6 | C.C.A. ^D @0°F | C.A. ^E @32°F | @ 25 Amps | @ 75 Amps | 5-Hr | 10-Hr | 20-Hr | 100-Hr | 100-Hr | 17 | 3600 |
| ь | _ | _ | 597 | 161 | 228 | 249 | 279 | 320 | 1.92 | 1.7 | |

CHARGING INSTRUCTIONS

| CHARGE | CHARGER VOLTAGE SETTINGS (AT 77°F/25°C) | | | | | |
|----------------------------------|---|-------|-------|-------|-------|--|
| SYSTEM VOLTAGE | 6V | 12V | 24V | 36V | 48V | |
| Maximum Charge Current (A) | 50% of C ₂₀ | | | | | |
| Absorption Voltage (2.40 V/cell) | 7.20 | 14.40 | 28.80 | 43.20 | 57.60 | |
| Float Voltage (2.25 V/cell) | 6.75 | 13.50 | 27.00 | 40.50 | 54.00 | |

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

| ADD | SUBTRACT |
|--|--|
| 0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F | 0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F |

OPERATIONAL DATA

| OPERATING TEMPERATURE | SELF DISCHARGE |
|---|--|
| -40°F to 140°F (-40°C to +60°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60% | Less than 3% per month depending on storage temperature conditions |

RECYCLE RESPONSIBLY









STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

| PERCENTAGE CHARGE | CELL | 6 VOLT |
|-------------------|------|--------|
| 100 | 2.14 | 6.42 |
| 75 | 2.09 | 6.27 |
| 50 | 2.04 | 6.12 |
| 25 | 1.99 | 5.97 |
| 0 | 1.94 | 5.82 |


TROJAN J305-AES PERFORMANCE





PERCENT CAPACITY VS. TEMPERATURE




BATTERY DIMENSIONS (shown with DT)








SELF DISCHARGE VS. TIME



TERMINAL TYPE



Battery Height with Terminal in Inches (mm) 14.09 (358) Torque Values in-lb (Nm) Connected to Stud: 95 - 105 (11 - 12) Connected to AP: 50 - 70 (6 - 8) **Bolt Size** 5/16"

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are
- The amount of named a patient value when value as a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. capacities are based on peak performance.

 The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.
- Dimensions may vary depending on type of handle or terminal, Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum. C.C.A. (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.
- E. C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2 CAL Clothoning Analysis the discharge lower in amperes which a reve, may regard basety of an inalitation to discounts at 32 V/Cell. This is sometimes referred to as an arine cranting amps @ 32°F or M.C.A. @ 32°F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.

- Batteries in storage should be charged when they decline to 75% State of Charge (SOC).
- Weight may vary.















Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

